

TECHNICAL DATA SHEET

2020

SOFT NATURAL RUBBER LININGS

October 1, 2010

Polycorp 2020 is a black 47A durometer soft natural rubber lining combining excellent corrosion resistance with good physical properties and abrasion resistance. A-I-E Cure.

Application Notes:

- **Skive** – use open skive construction
- **Repair** – Same or 2019 chemical cure.
- **Cured Durometer** – Shore A Durometer of top surface: 47 ± 5.
- **Spark Test** – Refer to section 13 of the Application Manual

Adhesive Notes:

See Section 9 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes.

For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C).

Use adhesives in well ventilated area and always consult the material safety data sheet for specific precautions.

<u>Coat</u>	<u>Polycorp Adhesive</u>	<u>Approved Equivalent</u>
1 st Coat on Metal	C-90 Primer	Chemlok 289
2 nd Coat on Metal	C-91 Intermediate	Chemlok 290
3 rd Coat on Metal	C-202S Tack	Chemlok 286
4 th Coat on lining	C-202S Tack	Chemlok 286

For distributors of Chemlok adhesives, see Section 9 of the Application Manual

Curing:

Cure time adjustments may be required to compensate for specific conditions. See Section 11 of the Application Manual for detailed instructions.

Autoclave Method – Up to 1/4” thickness:

1 hours @ 260°F/127°C (20 psi)

Autoclave Method – 1/2” thickness:

1 ½ hours @ 260°F/127°C (20 psi).

Internal Steam Method – Up to 1/4” thickness:

4 hours @ 260°F/127°C (20 psi) or

7 hours @ 240°F/116°C (10 psi).

Atmospheric Steam Method – Up to 1/4” thickness:

Minimum 20 hours @ 212°F/100°C.

Storage:

Store in a cool, dry area.

Shelf Life:

Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	60 days
Stored between 71 and 90°F	30 days
Do not store above 90°F (32°C)	

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual

TECHNICAL DATA SHEET

2020 Page 2 of 2

Typical Properties:

<u>Property</u>	<u>Value</u>	<u>ASTM Test Method</u>
Hardness (Face)	47 A \pm 5	D2240
Tensile Strength (min, psi)	3000	D412
Elongation at Break (min, %)	400	D412
Specific Gravity	1.11	D927
Adhesion to Metal (min, lbs)	25	D429
Maximum Operating Temperature for Optimum Service Life	71°C/160°F	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

PRECAUTIONS:

- When pressure curing, use air pressure cool down to 120°F/49°C before opening the tank.